

**TYPICAL APPLICATIONS**

- ◆ Suitable for high clarity injection molding and injection-stretch blow molding applications.
- ◆ Used for the production of Housewares and Clear Containers.

KEY CHARACTERISTICS

- ◆ Excellent Processability and flow-ability.
- ◆ Excellent Transparency.
- ◆ Good Impact Resistance.
- ◆ Food contact approval for specific applications (*refer to NATPET*)

PROCESSING METHOD

Injection Molding

QUALITATIVE

Test	Conditions	Method	Value	Unit
Basic				
Density		ISO 1183	0.900	g/cm ³
Melt Flow Rate (MFR)	230°C/2.16 kg	ISO 1133	40	g/10-min
Mechanical				
Flexural Modulus	1-mm/min	ISO 178	1,000	MPa
Tensile Stress at Yield	50-mm/min	ISO 527	28.0	MPa
Tensile Strain at Break		ISO 527	12	%
Notched Izod Impact Strength	23 °C	ISO 180/1A	6	kJ/m ²
Thermal				
Deflection Temperature Under Load	0.45 Mpa	ISO 75	90	°C
Optical				
Haze	1.0 mm	ASTM D 1003	6.0	%

Note: The above are typical data representing the product; not to be construed as analysis certificate or specifications

For further details about NATPET and its products, please visit the website at www.natpetpp.com

NATPET® products, marketed under the trade name Teldene®, are intended for the use by those customers and/or any other consumers, who undertake to become responsible to independently establish on their own the appropriateness of the product for its intended use, covering all safety and legally enacted requirements at the location of its projected use and the legal disposal practices thereof. The description of the product as given in this sheet shall under no circumstances be construed as warranty, express or implied including a warranty of merchandize fitness for a particular purpose. On behalf of NATPET, no one is authorized to make any such warranties, or take up on their own to assume such a liability. In case of product related claims, the sole and maximum remedy will be the physical substitution of the product or reimbursement of the purchase value, as per NATPET's options. Further claims based on consequential, secondary, castigatory, or extraordinary damages will in no way entertained by NATPET.

NATPET would like to advise its customers and other users that unless specifically stated the supplied products should not be used for applications in medical and/or pharmaceutical sectors.